

Gilsonit'nin (doğal asfalt) Özellikleri

NO	TEST	RESULT	TEST METHOD
1	ASH CONTENT,WT%	1%	ASTM-D3174
2	MOISTURE CONTENT,WT%	1%	ASTM-D3173
3	VOLATILE MATTER,WT%	63	ASTM-D3175
5	SOLUBILITY IS CS ₂ ,WT%	99	ASTM-D4
6	SPECIFIC GRAVITY @25 C	1.06	ASTM-D3289
7	NORMAL HEPHTAN INSOLUBLES,WT%	79	ASTM-D3279
8	COLOR IS MASS	BLACK	-----
9	COLOR IN STREAK OR POWDER	BLACK	-----
10	SOFTENING POINT,C	140-220	ASTM-D36
11	SULPHUR CONTENT	1%	ASTM-D6608
12	PENETRATION @25C	0	ASTM-D5
			200 SIEVE ANALYSIS API GRADE
1	+35 (500 MICRONS)	≤0.1	ASTM-D5291
2	+65 (212 MICRONS)	≤2.0	ASTM-D5291
3	+100 (150 MICRONS)	≤8	ASTM-D5291
4	+200 (74 MICRONS)	≤25	ASTM-D5291