

**Product Name: Bitumen 20/30****CAS No.:** 8052-42-4**HS Code:** 27132000

Property	Test Method	Unit	Typical Value
Penetration @ 25°C (100g, 5s)	ASTM D5	dmm	20 – 30
Softening Point (Ring & Ball)	ASTM D36	°C	55 – 63
Flash Point (Cleveland Open Cup)	ASTM D92	°C	> 250
Ductility @ 25°C	ASTM D113	cm	> 100
Solubility in Trichloroethylene	ASTM D2042	%	≥ 99.0
Loss on Heating	ASTM D6	%	≤ 0.5
Specific Gravity @ 25°C	ASTM D70	g/cm ³	1.01 – 1.06
Drop in Penetration After Heating	ASTM D5	%	≤ 20
Water Content	ASTM D95	%	Nil