



Product Name: Bitumen 115/25 (Oxidized Bitumen)

CAS No.: 64742-93-4

HS Code: 271320

Property	Typical Value	Test Method
Softening Point (°C)	110 – 120	ASTM D36 / EN 1427
Penetration (25°C, 0.1 mm)	15 – 30	ASTM D5 / EN 1426
Specific Gravity @ 25°C	1.00 – 1.10	ASTM D70
Loss on Heating (% wt)	≤ 0.5	ASTM D6
Flash Point (°C)	≥ 250	ASTM D92
Solubility in Trichloroethylene (%)	≥ 99.0	ASTM D2042
Ductility (cm @ 25°C)	≥ 1	ASTM D113