Basekim
Chemical Production Co.Ltd.

Product Name: Bitumen AH-70

CAS No.: 8052-42-4

HS Code: 27132000

Property	Test Method	Unit	Typical Value
Penetration @ 25°C (100g, 5s)	ASTM D5	dmm	40 – 60
Softening Point (Ring & Ball)	ASTM D36	°C	50 – 60
Ductility @ 15°C	ASTM D113	cm	≥ 100
Flash Point (Cleveland Open Cup)	ASTM D92	°C	≥ 230
Solubility in Trichloroethylene	ASTM D2042	%	≥ 99.0
Thin Film Oven Test (Mass Loss)	ASTM D6	%	≤ 1.0
Residue Penetration After TFOT	ASTM D5	%	≥ 50 of original
Dynamic Viscosity @ 60°C	ASTM D2171	Pa·s	≥ 3000
Kinematic Viscosity @ 135°C	ASTM D2170	cSt	≥ 350
Specific Gravity @ 25°C	ASTM D70	g/cm³	~1.03

İLKBAHAR MAH. GALİP ERDEM CD.FAHREDDIN PASA (613) SOKAK, NO.6, ÇANKAYA ANKARA/TURKEY
00903125147074
00903125147081
info@basekim.com
www.basekim.com