

**Product Name: Bitumen Cutback RC-30****CAS No.:** 8052-42-4**HS Code:** 27132000

Property	Typical Value	Test Method
Penetration (25°C, 0.1 mm)	25 – 35	ASTM D5 / EN 1426
Softening Point (°C)	55 – 70	ASTM D36 / EN 1427
Ductility (cm at 25°C)	≥ 40	ASTM D113
Specific Gravity	1.01 – 1.05	ASTM D70
Flash Point (°C)	≥ 230	ASTM D92
Solubility in Carbon Disulfide (%)	≥ 99	ASTM D2042
Viscosity (at 60°C, Poise)	300 – 1000	ASTM D2171
Penetration Index	-2.0 to -1.0	Calculated
Moisture Content	Max 0.1%	ASTM D95
Ash Content	Max 0.1%	ASTM D482