

**Product Name: Bitumen Cutback RC-800****CAS No.:** 8052-42-4**HS Code:** 27132000

Property	Test Method	Unit	Typical Value
Kinematic Viscosity @ 60°C	ASTM D2170	cSt	800 – 1600
Flash Point (Tag Open Cup)	ASTM D3143	°C	≥ 27
Distillation to 360°C (Residue)	ASTM D402	%	≥ 55
Water Content	ASTM D95	%	≤ 0.2
Solubility in Trichloroethylene	ASTM D2042	%	≥ 99.0
Penetration of Residue @ 25°C	ASTM D5	dmm	100 – 250
Ductility of Residue @ 25°C	ASTM D113	cm	≥ 100
Specific Gravity @ 25°C	ASTM D70	g/cm ³	~1.00
Loss on Heating	ASTM D6	%	≤ 1.0