

**Product Name: Oxidized Bitumen 105/35****CAS No.:** 64742-93-4**HS Code:** 271320

Property	Unit	Typical Value
Grade	–	Oxidized Bitumen 105/35
Penetration @ 25°C	dmm	30 – 40
Softening Point (Ring & Ball)	°C	100 – 110
Flash Point (COC)	°C	> 250
Loss on Heating	% wt	< 0.5
Ductility @ 25°C	cm	< 1
Solubility in Trichloroethylene	%	> 99
Specific Gravity @ 25°C	–	1.00 – 1.10
Drop Point	°C	~230
Color	–	Black
Form	–	Solid (Block, Slab, Granule, Drums)