



Product Name: Bitumen VG 30

CAS No.: 8052-42-4

HS Code: 27132000

Property	Test Method	Unit	Typical Value
Absolute Viscosity @ 60°C	ASTM D2171	poise	> 3000
Kinematic Viscosity @ 135°C	ASTM D2170	cSt	≥ 350
Penetration @ 25°C (100g, 5s)	ASTM D5	dmm	50 – 70
Softening Point (R&B)	ASTM D36	°C	47 – 55
Flash Point (COC)	ASTM D92	°C	> 220
Ductility @ 25°C	ASTM D113	cm	> 75
Solubility in Trichloroethylene	ASTM D2042	%	> 99
Loss on Heating (Thin Film Oven Test)	ASTM D6	%	< 1.0